# Key dimensions and material information

## BI300 Implants & BA400 Abutments

All sterile products are for single use only.

**Implants:** The BI300 Implants and BA400 Abutments are made of commercially pure grade 1 to 4 unalloyed titanium (ASTM standard F-67) which has the following chemical composition.

Element	Nitrogen (N)	Carbon (C)	Hydrogen (H)	Iron (Fe)	Oxygen (O)	Titanium (Ti)
Composition % by weight	max 0.03	max 0.08	max 0.015	max 0.20	max 0.40	Balance

The abutment screw is made of titanium alloy, grade 5 (ASTM standard F-136).

**Abutments:** The BA400 Abutments are coated with a hydroxyapatite layer, Ca5(PO4)3(OH) according to ISO 13779-2. The coating is applied by a plasma-spray technique and has a mean thickness of approximately  $80\mu m$ . The surface roughness (Ra) is approximately  $7\mu m$ .

**Drills:** All drills are made of hardened stainless steel (WS 1.4197). The spacer on the Conical guide drill 3+4 mm is made of Celanex 2401 MT.

# NOTE:

Images are not to scale.



93329 BIA400 Implant 4mm with Abutment 6mm

Weight: 0.7 g



93330 BIA400 Implant 4mm with Abutment 8mm

Weight: 0.9 g



93331 BIA400 Implant 4mm with Abutment 10mm

Weight: 1.3 g



93332 BIA400 Implant 4mm with Abutment 12mm

Weight: 1.5 g



93333 BA400 Abutment 6mm

Weight: 0.5 g



93334 BA400 Abutment 8mm

Weight: 0.7 g



93335 BA400 Abutment 10mm

Weight: 1.0 g



93336 BA400 Abutment 12mm

Weight: 1.3 g

### -

### NOTE:

Images are not to scale.



92128 BI300 Implant 3mm

Weight: 0.19 g



92129 BI300 Implant 4mm

Weight: 0.26 g



92136

Cover screw conical

Weight: 0.04 g



92139 Guide drill 3+4 mm Ø 2.3 mm

Weight: 1.1 g



92140

Widening drill 3mm with countersink

Weight: 1.7 g



92141

Widening drill 4mm with countersink

Weight: 1.8 g

Cochlear Bone Anchored Solutions AB Konstruktionsvägen 14, SE - 435 33 Mölnlycke, Sweden Tel: +46 31 792 44 00 Fax: +46 31 792 46 95

Cochlear Ltd (ABN 96 002 618 073) 1 University Avenue, Macquarie University NSW 2109, Australia Tel: +61 2 9428 6555 Fax: +61 2 9428 6352 Cochlear Americas 13059 E Peakview Avenue, Centennial, CO 80111, USA Tel: +1 303 790 9010 Fax: +1 303 792 9025 Cochlear AG EMEA Headquarters, Peter Merian-Weg 4, 4052 Basel, Switzerland Tel: +41 61 205 0404 Fax: +41 61 205 0405

www.cochlear.com

